

इंटरनेट

मानक

Disclosure to Promote the Right To Information

Whereas the Parliament of India has set out to provide a practical regime of right to information for citizens to secure access to information under the control of public authorities, in order to promote transparency and accountability in the working of every public authority, and whereas the attached publication of the Bureau of Indian Standards is of particular interest to the public, particularly disadvantaged communities and those engaged in the pursuit of education and knowledge, the attached public safety standard is made available to promote the timely dissemination of this information in an accurate manner to the public.

“जानने का अधिकार, जीने का अधिकार”

Mazdoor Kisan Shakti Sangathan

“The Right to Information, The Right to Live”

“पुराने को छोड़ नये के तरफ”

Jawaharlal Nehru

“Step Out From the Old to the New”

IS 11014-4 (1989): Piezoelectric Ceramic Materials, Part 4:
Type 5 H [LITD 5: Semiconductor and Other Electronic
Components and Devices]



“ज्ञान से एक नये भारत का निर्माण”

Satyanarayan Gangaram Pitroda

“Invent a New India Using Knowledge”



“ज्ञान एक ऐसा खजाना है जो कभी चुराया नहीं जा सकता है”

Bhartrhari—Nitiśatakam

“Knowledge is such a treasure which cannot be stolen”

BLANK PAGE



Indian Standard
**SPECIFICATION FOR
PIEZOELECTRIC CERAMIC MATERIALS**

PART 4 TYPE 5H

भारतीय मानक
परावैद्युत चोनी मिट्टी सामग्रियों को विशिष्ट
भाग 4 टाइप 5 एच

UDC 621.372.412 : 666.655

© BIS 1990

BUREAU OF INDIAN STANDARDS
MANAK BHAVAN, 9 BAHADUR SHAH ZAFAR MARG
NEW DELHI 110002

January 1990

Price Group 1

Piezoelectric Devices for Frequency Control and Selection Sectional Committee, LTDC 12

FOREWORD

This Indian Standard (Part 4) was adopted by the Bureau of Indian Standards on 23 June 1989, after the draft finalized by the Piezoelectric Devices for Frequency Control and Selection Sectional Committee had been approved by the Electronics and Telecommunication Division Council.

This standard shall be read in conjunction with IS 11014 (Part 1) : 1984 'Specification for piezoelectric ceramic materials: Part 1 General aspects and methods of measurements'. The other parts of this standard are:

(Part 2) : 1984 Types 1 and 5

(Part 3) : 1985 Types 4 and 8

For the purpose of deciding whether a particular requirement of this standard is complied with, the final value, observed or calculated, expressing the result of a test or analysis, shall be rounded off in accordance with IS 2 : 1960 'Rules for rounding off numerical values (*revised*)'. The number of significant places retained in the rounded off value should be the same as that of the specified value in this standard.

Indian Standard

SPECIFICATION FOR PIEZOELECTRIC CERAMIC MATERIALS

PART 4 TYPE 5H

1 SCOPE

1.1 This standard (Part 4) specifies detail requirements for the characteristics of piezoelectric ceramic materials of Type 5H.

2 REFERENCE

IS No.	Title
IS 11014 (Part 1) : 1984	Specification for piezoelectric ceramic materials: Part 1 General aspects and methods of measurements

3 TYPE DESIGNATION

3.1 For type designation, see 3 of IS 11014 (Part 1) : 1984.

3.2 Type 5H

Modified 'lead zirconate titanate' material having soft ferro-electric grade, exceptionally high dielectric constant, electromechanical high dielectric constant, electromechanical coupling coefficient and charge sensitivity suitable for use in the following applications:

- a) Phonograph pick up elements;
- b) Underwater hydrophones;

c) Microphones; and

d) Fine movement control application, etc.

4 TEST SPECIMENS

4.1 In general, practical dimensions used in ceramic elements may not be suitable for the measurement of many parameters. To determine these parameters accurately, it is essential to have test specimen of three different configurations as follows:

- a) $l \geq 2.5 w, t, D$;
- b) $l \geq 3.5 w, t$; or
- c) $D \geq 10 t$

where

l = length,

w = width

t = thickness, and

D = diameter of the disc.

5 PARAMETERS

5.1 Parameters with tolerance for piezoelectric ceramic material Type 5H are given in Table 1.

Table 1 Parameters with Tolerance for Piezoelectric Ceramic Material Type 5H

Sl No.	Parameters	Symbols	Value	Tolerance in percent
(1)	(2)	(3)	(4)	(5)
i)	Density (Min) (10^3 kg/m^3)	d	7.5	—
ii)	Dielectric constant	K_s^T	3 300	± 10
iii)	Dissipation factor (Max)	$\tan \delta$	0.025	—
iv)	Resistivity (ohm) (approx)	ρ	$> 10^{11}$	—
v)	Planar coupling coefficient	k_p	0.60	± 10
vi)	Piezoelectric charge constant $\times 10^{-12} \text{ C/N}$	d_{33}	580	± 10
vii)	Piezoelectric voltage constant $\times 10^{-12} \text{ Vm/N}$	g_{33}	17.5	± 10
viii)	Frequency constant (Hz)	N_{st}	2 050	± 10
ix)	Mechanical quality factor	Q_m	60	± 10
x)	Curie temperature ($^{\circ}\text{C}$)	θ_C	190	—

Standard Mark

The use of the Standard Mark is governed by the provisions of the *Bureau of Indian Standards Act, 1986* and the Rules and Regulations made thereunder. The Standard Mark on products covered by an Indian Standard conveys the assurance that they have been produced to comply with the requirements of that standard under a well defined system of inspection, testing and quality control which is devised and supervised by BIS and operated by the producer. Standard marked products are also continuously checked by BIS for conformity to that standard as a further safeguard. Details of conditions under which a licence for the use of Standard Mark may be granted to manufacturers or producers may be obtained from the Bureau of Indian Standards.

Bureau of Indian Standards

BIS is a statutory institution established under the *Bureau of Indian Standards Act, 1986* to promote harmonious development of the activities of standardization, marking and quality certification of goods and attending to connected matters in the country.

Copyright

BIS has the copyright of all its publications. No part of these publications may be reproduced in any form without the prior permission in writing of BIS. This does not preclude the free use, in the course of implementing the standard, of necessary details, such as symbols and sizes, type or grade designations. Enquiries relating to copyright be addressed to the Director (Publications), BIS.

Revision of Indian Standards

Indian Standards are reviewed periodically and revised, when necessary and amendments, if any, are issued from time to time. Users of Indian Standards should ascertain that they are in possession of the latest amendments or edition. Comments on this Indian Standard may be sent to BIS giving the following reference:

Doc : No. LTDC 12 (1172)

Amendments Issued Since Publication

Amend No.	Date of Issue	Text Affected

BUREAU OF INDIAN STANDARDS

Headquarters:

Manak Bhavan, 9 Bahadur Shah Zafar Marg, New Delhi 110002
Telephones : 331 01 31, 331 13 75

Telegrams : Manaksanstha
(Common to all Offices)

Regional Offices:

Central : Manak Bhavan, 9 Bahadur Shah Zafar Marg NEW DELHI 110002	{ 331 01 31 331 13 75
Eastern : 1/14 C.I.T. Scheme VII M, V.I.P. Road, Maniktola CALCUTTA 700054	36 24 99
Northern : SCO 445-446, Sector 35-C, CHANDIGARH 160036	{ 2 18 43 3 16 41
Southern : C.I.T. Campus, IV Cross Road, MADRAS 600113	{ 41 24 42 41 25 19 41 29 16
Western : Manakalaya, E9 MIDC, Marol, Andheri (East) BOMBAY 400093	6 32 92 95
Branches : AHMADABAD. BANGALORE. BHOPAL. BHUBANESHWAR. GUWAHATI. HYDERABAD. JAIPUR. KANPUR. PATNA. TRIVANDRUM.	